

**Amendments to the Abstract**

Please amend the ABSTRACT as follows:

**ABSTRACT**

Shielded cable devices are formed of a conductive loaded resin-based material. Non-insulated conductors with shields, coaxial shielded cables, twisted pair shielded cables, and multi-wire shielded cables are described. The conductive loaded resin-based material includes ~~comprises~~ micron conductive powder(s), conductive fiber(s), or a combination of conductive powder and conductive fibers in a base resin host. The ratio of the weight of the conductive powder(s), conductive fiber(s), or a combination of conductive powder and conductive fibers to the weight of the base resin host is between about 0.20 and 0.40. The micron conductive powders are formed from non-metals, such as carbon, graphite, that may also be metallic plated, ~~or the like,~~ or from metals such as stainless steel, nickel, copper, silver, that may also be metallic plated, ~~or the like,~~ or from a combination of non-metal, plated, or in combination with, metal powders. ~~The micron conductor fibers preferably are of nickel plated carbon fiber, stainless steel fiber, copper fiber, silver~~

~~fiber, or the like. The conductive loaded resin based conductive shield of the shielded cable devices can be formed using methods such as injection molding compression molding or extrusion. The conductive loaded resin based material used to form the conductive shield of the shield cable devices can also be in the form of a thin flexible woven fabric that can readily be cut to the desired shape.~~